This Page Is Inserted by IFW Operations and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

As rescanning documents will not correct images, please do not report the images to the Image Problems Mailbox.

THIS PAGE BLANK (USPFO)



WORLD INTELLECTUAL PROPERTY ORGANIZATION International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 7: C09C 3/12, C08K 9/06, G02B 1/11		(11) International Publication Number: WO 00/27931		
		(43) International Publication Date: 18 May 2000 (18.05.00)		
(21) International Application Number: PCT/NL (22) International Filing Date: 4 November 1999 ((81) Designated States: CN, KR, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).			
(30) Priority Data: 10/316144 6 November 1998 (06.11.98	3)	Published With international search report.		
(71) Applicants (for all designated States except US): D [NL/NL]; Het Overloon 1, NL-6411 TE Heerlen (CORPORATION [JP/JP]; JSR Building, 2-11-24 Chuo-ku, Tokyo 104-8410 (JP). JAPAN FINE CC CO. LTD. [JP/JP]; 2-11-24, Tsukiji, Chuo-ki 104-8410 (JP).	R ji, SS			
(72) Inventors; and (75) Inventors/Applicants (for US only): YASHIRO [JP/JP]; 2-13-28-515, Kawaguchi, Tsuchiura 360 (JP). ERIYAMA, Yuichi [JP/JP]; 2-18-3 Umezono, Tsukuba, Ibaraki 305 (JP). NISHIWA [JP/JP]; 2-19-12-411, Toride, Ibaraki (JP). Takashi [JP/JP]; 5-22-9, Kamiya, Ushiku 300-12	ki 4, ao			
(74) Agent: DEN HARTOG, Jeroen, Hendrikus, Josep Patents & Trademarks, P.O. Box 9, NL-6160 M (NL).	M en			

(54) Title: RADIATION-CURABLE METAL PARTICLES AND CURABLE RESIN COMPOSITIONS COMPRISING THESE PARTICLES

(57) Abstract

To provide a liquid curable resin composition which can produce transparent cured products with a high refractive index, high hardness, and superior abrasion resistance, and can be suitably used as a coating material. A liquid curable resin composition comprising:

(A) a poly-functional (meth)acrylic compound having at least three (meth)acryloyl groups in the molecule; (B) a reaction product obtained by the reaction of a compound having a polymerizable unsaturated group and alkoxysilyl group in the molecule and particles metal oxide, the metals being selected from the group consisting of zirconium, antimony, zinc, tin, cerium, and titanium; and (C) a radiation polymerization initiator.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
ΛT	Austria	FR	France	LU	Luxembourg	SN	Senegal
ΛU	Australia	GA	Gabon	LV	Larvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CC	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
СН	Switzerland	KG	Kyrgyzstan	NO	Norway	zw	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's	NZ	New Zealand		
CM	Cameroon		Republic of Korea	Pl.	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		
I							

WO 00/27931 PCT/NL99/00678

- 1 -

5

RADIATION-CURABLE METAL PARTICLES AND CURABLE RESIN COMPOSITIONS COMPRISING THESE PARTICLES

10 Field of the Invention

The present invention relates to radiationcurable metal particles comprising a radiation-curable
group linked by a silyl group to a metal and, to a
liquid curable resin composition comprising a polyfunctional (meth) acrylic compound and these metal oxide
particles. More particularly, the present invention
relates to a liquid curable resin composition which can
produce cured products with a high refractive index by
application to fabricated plastic articles or films and
can also produce anti-reflection films.

Background of Invention

Deen applied as means for protecting surfaces of

fabricated plastic materials such as plastic optical
parts, touch panels, and film-type liquid crystal
elements, as well as coated surfaces such as floors and
walls inside buildings. UV curable acrylic-type hard
coat materials such as polyester acrylate, urethane

acrylate, and epoxy acrylate have been used as such
hard coat materials. When used alone, however, these
hard coat materials could not sufficiently improve mar

- 2 -

5

resistance, slip characteristics, and stain resistance of the above-mentioned plastic surfaces and coated surfaces.

A method of adding inorganic fillers such as silica or organic fillers such as polyethylene powder and polycarbonate powder and a method of adding additives such as silicone are well known as the method for improving mar resistance, slip characteristics, and stain resistance of fabricated plastic surfaces.

10 However, the method of adding inorganic or organic fillers has drawbacks such as an increased haze value and impaired appearance of resulting coating films. The method of adding silicone can improve slip characteristics of coating surfaces, but not mar resistance due to abrasive wheels. In addition, a hard coat applied to a touch panel or the like requires an after-treatment step with alkali etching. This may involve hydrolysis of commonly used silicone additives with alkali, resulting in impaired appearance of coatings or peeling of coatings from fabricated plastic materials.

With regard to a thermosetting resin
material with a high refractive index, Japanese Patent
Publication No. 12489/1990 discloses a high refractive

25 index resin used for lenses. The resin comprises a
polymer obtained by the reaction of a vinyl compound
and an urethanized (meth)acrylic monomer which is
obtained by the reaction of a (meth)acrylic monomer
having a halogen substituted aromatic ring and a

30 polyfunctional isocyanate compound. Although the resin
has a high refractive index, its abrasion resistance is

- 3 -

insufficient.

30

On the other hand, with regard to a photopolymerizable cross-linking coating materials, Japanese Patent Application Laid-open No. 169833/1987 discloses a photocurable monomer comprising polyacrylate of dipentaerythritol. Coatings with sufficient hardness can be obtained in a short period of time using this monomer. However, because the coatings have a refractive index of 1.55 or less, the 10 monomer may produce interference stripes if coated over the substrate with a high refractive index such as polycarbonate, polyester carbonate, polyethylene terephthalate, or poly-1,4-cyclohexane dimethylene terephthalate. Thus, this material is inadequate for use with optical products requiring high resolution. 15

Problems to be Solved by the Invention

An object of the present invention is to provide a liquid curable resin composition which can produce transparent cured products with a high refractive index, high hardness, and superior abrasion resistance, and can be suitably used as a coating material.

Another object of the present invention is

to provide a liquid curable resin composition suitable
for producing a hard coat over the surface of
fabricated plastic materials.

Other objects and features of the present invention will become apparent from the following detailed description of the present invention.

30

Summery of the Invention

The present invention provides radiation-curable metal particles comprising a radiation-curable group linked by a silyl group to a metal, in particular where said metal is not inclusive of silicon metal.

Also provided are methods to prepare such particles.

In addition, the present invention provides compositions that comprise the above-noted particles. Preferred compositions provided by the present invention are compositions that, after radiation cure, provide products of high transparency, low haze, and a

Furthermore, the present invention provides articles made by curing the above compositions,

including articles comprising coatings and films formed from such compositions. In particular articles having antireflection properties are provided.

Detailed Description of the Invention

refractive index of more than 1.55.

20 Herein certain terms are used to define certain chemical aspects. These terms are defined below.

A (meth)acrylic compound is a compound comprising a (meth)acryloyl group, whereby it is noted that a (meth)acrylol group, by definition, comprises an unsaturated bond.

When reference is made to groups in the periodic table of elements, reference is made to the periodic table appearing on the inside front cover of "CRC Handbook of Chemistry and Physics", 78th ed. 1997-1998, and to the "New Notation" noted thereon.

Consequently, the groups are numbered in arabic notation, for example group 11 is the group consisting of copper, silver and gold, group 2 is the group that includes magnesium, calcium and barium etc.

5 Furthermore, in this application, group 3 is considered to include elements 57-71 and elements 89-103, i.e. the lanthanides and actinides.

The present invention provides a radiation-curable metal particle comprising a radiation-curable group linked by a silyl group to a metal, which hereinafter will also be referred to as "component B". It will be appreciated by one of ordinary skill in the art that "component B" may refer to a single particle, multiple particles, or a mixture of particles.

The present invention further provides compositions comprising these particles. Such radiation-curable compositions may be any suitable radiation-curable composition, and may further comprise a (meth)acrylic compound (hereinafter also referred to as "component (A)"). The composition may, independent of the presence of component (A), also comprise a radiation polymerization initiator (hereinafter also referred to as "component (C)").

Component (A) can be any suitable

(meth)acrylic compound. Preferably, component (A)

comprises at least three (meth)acryloyl groups in the

molecule, more preferably from 3 to 10 (meth)acryloyl

groups, even more preferably from 4 to 10

(meth)acryloyl groups, and most preferably from 4 to 8

(meth)acryloyl groups.

Given as examples of such a (meth)acrylic compound are trimethylolpropane tri(meth)acrylate, trimethylolpropane trioxyethyl (meth)acrylate, tris(2-hydroxyethyl)isocyanurate tri(meth)acrylate,

pentaerythritol tri(meth)acrylate, pentaerythritol tetra(meth)acrylate, dipentaerythritol hexa(meth)acrylate, and the like.

As examples of commercially available products of the (meth)acrylic compound having at least three (meth)acryloyl groups in the molecule, Kayarad DPHA, DPCA-20, DPCA-30, DPCA-60, DPCA-1 20, D-310, D-330, PET-30, GPO-303, TMPTA, THE-330, TPA-330 (manufactured by Nippon Kayaku Co., Ltd.), Aronix M-315, M-325 (manufactured by Toagosei Co., Ltd.), and the like can be given.

The proportion of the (meth)acrylic compound having at least three (meth)acryloyl groups in the molecule used as the component (A) in the composition of the present invention is in the range preferably from 1 to 99 wt%, more preferably from 10 to 90 wt%, and particularly preferably from 30 to 70 wt%. The number of (meth)acryloyl groups in the molecule is preferably from 4 to 10, and more preferably from 4 to 8.

The particles of component (B) comprise a radiation-curable group linked by a silyl group to a metal. The metal can be any suitable metal, and is preferably a metal selected from the metals listed in groups 2-16 from the periodic table of elements

exclusive of silicon metal. Preferably the metal is selected from the metals listed in groups 3-4 and 12-15

- 7 -

10

25

30

from the periodic table of elements (exclusive of silicon metal). In particular it is preferred that the metal is selected from the group consisting of zirconium, titanium, antimony, zinc, tin, indium, cerium and aluminium, and most preferably the metal is selected from the group consisting of zirconium, antimony, zinc and cerium.

The silyl group is preferably a substituted silyl group. The substituted silyl group may be any suitable silyl group. Preferably, the substituted silyl group comprises a urethane group, a thiorethane group and/or an alkoxy group. Preferably, the silyl group comprises at least a urethane group.

The silyl group may be derived from

compounds having at least one alkoxysilyl group and
mercapto group in the molecule, as noted herein below,
and such compounds reacted with the isocyanates noted
herein below.

In a composition that comprises both

component (A) and component (B), the proportion of
component (B) is preferably from 1 to 99 wt%, more
preferably from 10 to 90 wt%, and particularly
preferably from 30 to 70 wt%, relative to the total
weight of the composition.

When component (B) is a mixture of particle 5, preferably at least 90 wt%, more preferably at least 95%, and most preferably at least 99 wt% of the total metals (excluding the silicon in the silyl group) in component (B) is selected from the group consisting of zirconium, titanium, antimony, zinc, tin, indium, cerium and aluminium.

10

15

20

25

30

Component (B) may be a reaction product.

The reaction product used as the component

(B) is obtained by the reaction of an organosilicon compound having a polymerizable unsaturated group and alkoxysilyl group in the molecule and metal oxide particles, wherein the major components of metal oxide particles are oxide of metals selected from the group consisting of zirconium, titanium, antimony, zinc, tin, indium, cerium, and aluminum. The proportion of the reaction product contained in the composition of the present invention as the component (B) is preferably from 1 to 99 wt%, more preferably from 10 to 90 wt%, and particularly preferably from 30 to 70 wt%. The reaction is carried out preferably in the presence of water.

The reaction product used as the component (B) in the present invention can be prepared by a method including at least an operation of mixing the organosilicon compound and metal particles. The amount of residual organosilicon compounds immobilized on metal oxide particles is preferably 0.01 wt% or more, more preferably 0.1 wt% or more, and most preferably 1 wt% or more. If the amount of residual organosilicon compounds immobilized on metal oxide particles is less than 0.01 wt%, dispersibility of the reaction product containing metal oxide particles in the composition of the present invention may be insufficient, which may result in lack of transparency and abrasion resistance of the composition. The proportion of organosilicon compounds in the raw material composition to produce the component (B) is preferably 10 wt% or more, and

20

25

30

more preferably 30 wt% or more. If proportion of organosilicon compounds is less than 10 wt%, filmforming capability of the resulting composition may be poor. The proportion of metal oxide particles in the raw material composition for the component (B) is preferably 50 wt% or less, and more preferably 20 wt% or less. Dispersibility, transparency, and abrasion resistance of the resulting composition may be insufficient, if the amount of the metal oxide

10 particles in the raw material composition for preparing component (B) is more than 50 wt%.

Preferably the organosilicon compound possesses a polymerizable unsaturated group and alkoxysilyl group in the molecule. As preferable examples of the polymerizable unsaturated group, acrylic group, vinyl group, and styryl group can be given. As an alkoxysilyl group, the group which can be hydrolyzed in the presence of water or a hydrolysis catalyst is desirable. In addition, the organosilicon compound may contain at least one bond selected from an ester group, ether group, urethane group, sulfide group, and thiourethane group in the molecule. The organosilicon compound preferably comprises at least one polymerizable unsaturated group, urethane bond group, and alkoxysilyl group as its constituents. The alkoxysilyl group is the component which combines with adsorption water existing on the surface of metal oxide particles by a hydrolysis-condensation reaction. The polymerizable unsaturated group is the component of which the molecules chemically cross-link among themselves by an addition polymerization reaction in

the presence of reactive radicals. The urethane bond group is a constitutional unit which bonds the molecules having an alkoxysilyl group and the molecules having a polymerizable unsaturated group directly or via other molecules. At the same time, the urethane bond group creates a moderate cohesive force among molecules due to hydrogen bonds, thereby providing the cured products made from the composition of the present invention with excellent mechanical strength, superior adhesion with substrates, high heat resistance, and the like.

As examples of preferable organosilicon compounds, the compounds shown by the following formula (1) can be given.

15

20

25

10

$$R^{2} = SL - R^{2} \left(S - C - NH - R^{4}\right) NH - C - \left(O - X - O - C - NH - R^{4} - NH - C\right) R^{2} - (Y),$$
(1)

wherein R^1 is a hydrogen atom or a mono-valent organic group having from 1 to 8 carbon atoms, such as methyl, ethyl, propyl, butyl, phenyl, or octyl group; R^2 is a hydrogen atom or an alkyl group having from 1 to 3 carbon atoms; and m is 1, 2 or 3. As examples of trimethoxysilyl groups represented by the formula, $(RO^1)_m R^2_{3-m} Si$, triethoxysilyl group, triphenoxysilyl group, methyldimethoxysilyl group, dimethylmethoxysilyl group, and the like can be given, with preferred groups being trimethoxysilyl group and triethoxysilyl group.

A structural unit represented by the formula, $-(C=O)NH-R^4-NH(C=O)O-X-O]_p-$, is introduced to extend the molecular chain into the structure shown by the abovementioned formula (1). R3 is a divalent organic group having from 1 to 3 carbon atoms. R4, which may be either 5 the same with or different from R³, is a divalent organic group and selected from divalent organic groups with a molecular weight from 14 to 10,000, preferably from 78 to 1,000, for example, a linear polyalkylene group such as methylene, ethylene, propylene, 10 hexamethylene, octamethylene, and dodecamethylene groups; alicyclic or polycyclic divalent organic groups such as cyclohexylene and norbornylene groups; divalent aromatic groups such as phenylene, naphthylene, biphenylene, and polyphenylene groups; and alkyl group 15 or aryl group substitution products of these groups. These divalent organic groups may further contain atomic groups containing elements other than carbon atoms and hydrogen atoms. p and q in the above formula are 0 or 1. X is a divalent organic group, and more 20 particularly, a divalent organic group originating from the compound having an active hydrogen atom which can react with an isocyanate group in the molecule by the addition reaction. Given as examples are divalent organic groups obtained by removing two active hydrogen 25 atoms from the compound such as a polyalkylene glycol, polyalkylene thioglycol, polyester, polyamide, polycarbonate, polyalkylene diamine, polyalkylene dicarboxylic acid, polyalkylene diol, or polyalkylene dimercaptan. R^{5} is an organic group with a valency of 30 (n+1). Such an organic group is preferably selected

WO 00/27931

10

from linear, branched, or cyclic saturated hydrocarbon groups, unsaturated hydrocarbon groups, and alicyclic groups. Y in the above formula represents a mono-valent organic group having a polymerizable unsaturated group which causes a cross-linking reaction to occur among the molecules in the presence of reactive radicals, such as, for example, acryloxy group, methacryloxy group, vinyl group, propenyl group, butadienyl group, styryl group, ethynyl group, cinnamoyl group, maleate group, acrylamide group, and the like. Among these, acryloxy group is desirable. n is a positive integer preferably from 1 to 20, and more preferably from 1 to 10, and particularly preferably from 3 to 5.

The organosilicon compound used in the present invention can be prepared, for example, by (1) 15 an addition reaction of an alkoxysilane having a mercapto group (i.e. a mercaptoalkoxysilane), a polyisocyanate compound, and an active hydrogen groupcontaining polymerizable unsaturated compound which possesses an active hydrogen which can cause an 20 addition reaction to occur with an isocyanate group; (2) a direct reaction of an isocyanate compound having an isocyanate group and an alkoxysilyl group in the molecule with an active hydrogen-containing polymerizable unsaturated compound; or (3) an addition 25 reaction of a compound having a polymerizable unsaturated group and an isocyanate group in the molecules and a mercaptoalkoxysilane or aminosilane compound.

The following methods can be given as examples of the method using a mercaptoalkoxysilane as

a raw material.

Method (a):

A method comprising reacting a

5 mercaptoalkoxysilane and a polyisocyanate compound to
produce an intermediate which contains an alkoxysilyl
group, -S(C=0)NH- bonding group, and isocyanate group
in the molecule, and reacting the isocyanate in the
intermediate compound and an active hydrogen-containing
polymerizable unsaturated compound to combine this
unsaturated compound via a urethane group.

Method (b):

25

A method of reacting a polyisocyanate

compound and an active hydrogen-containing
polymerizable unsaturated compound to produce an
intermediate containing a polymerizable unsaturated
group, urethane bond group, and isocyanate group in the
molecule, and reacting this intermediate with a

20 mercaptoalkoxysilane to combine the mercaptoalkoxysilane via a -S(C=O)NH- group.

In above-mentioned method (a) or (b), a linear, cyclic, or branched compound having two or more active hydrogen atoms which is reactive with an isocyanate by an addition reaction in the molecule can be used additionally. Such a compound can extend the length of the chain of the alkoxysilane compound obtained by the reaction with a polyisocyanate compound via a urethane bond.

The compounds having at least one alkoxysilyl group and mercapto group in the molecule

can be given as examples of the alkoxysilane which can form the -S(C=0)NH- bond by the reaction with an isocyanate group in the preparation of the compound shown by the above-mentioned formula (1).

Given as examples of such compounds are 5 mercaptoalkoxysilanes such as mercaptopropyltrimethoxysilane, mercaptopropyltriethoxysilane, mercaptopropylmethyldiethoxysilane, mercaptopropyldimethoxymethylsilane, 10 mercaptopropylmethoxydimethylsilane, mercaptopropyltriethoxysilane, mercaptopropyltriphenoxysilane, and mercaptopropyltributoxysilane. Of these, preferable compounds are mercaptopropyltrimethoxysilane and 15 mercaptopropyltriethoxysilane. As an example of commercially available mercaptoalkoxysilane, SH6062 manufactured by Dow Corning Toray Silicone Co., Ltd. can be given. These mercaptoalkoxysilanes can be used either individually or in combinations of two or more. 20 As other mercaptoalkoxysilanes, an addition product of an amino substituted alkoxysilane and epoxy group substituted mercaptan, an addition product of an epoxy silane and α, ω -dimercapto compound, and the like can be 25 given.

The isocyanate compound used for preparing the organosilicon compounds can be selected from the compounds having a linear saturated hydrocarbon, cyclic saturated hydrocarbon, or aromatic hydrocarbon structure. Such isocyanate compounds can be used either individually or in combinations of two or more. The

number of isocyanate groups in a molecule is usually from 1 to 30, and preferably from 2 to 10. If more than 30, the viscosity of the products increases, resulting in lowered processability.

- Given as examples of such a isocyanate compound are linear hydrocarbon isocyanate compounds such as 3-trimethoxysilylpropane isocyanate, 3-triethoxysilylpropane isocyanate, 3-methacryloxypropyl isocyanate, tetramethylene diisocyanate, hexamethylene diisocyanate, and 2,2,4-trimethylhexamethylene diisocyanate; cyclic saturated hydrocarbon isocyanate compounds such as isophorone diisocyanate, dicyclohexylmethane diisocyanate, methylenebis (4-cyclohexylmethane diisocyanate, methylenebis (4-cyclohexylisocyanate), hydrogenated diphenylmethane diisocyanate, hydrogenated xylene diisocyanate, hydrogenated toluene diisocyanate, and 1,3-
- hydrogenated toluene diisocyanate, and 1,3bis(isocyanatemethyl) cyclohexane; and aromatic hydrocarbon isocyanate compounds such as 2,4-tolylene diisocyanate, 2,6-tolylene diisocyanate, 1,3-xylylene
- diisocyanate, 1,4-xylylene diisocyanate, p-phenylene diisocyanate, 3,3'-dimethyl-4,4'-diphenylmethane diisocyanate, diphenylmethane-4,4'-diisocyanate, 4,4'-biphenylene diisocyanate, 6-isopropyl-1,3-phenyl diisocyanate, 4-diphenylpropane diisocyanate, lysine
- 25 diisocyanate, 1,5-naphthalene diisocyanate, and polyisocyanates of polydiphenylmethane.

Among these, preferable compounds are cyclic saturated hydrocarbon polyisocyanate compounds and aromatic hydrocarbon polyisocyanate compounds, and more preferable compounds are cyclic saturated hydrocarbon polyisocyanate compounds. Specific examples

of particularly preferred polyisocyanate compounds are 3-trimethoxysilylpropane isocyanate, 3-triethoxysilylpropane isocyanate, isophorone diisocyanate, hydrogenated xylene diisocyanate, and hydrogenated toluene diisocyanate. Given as examples of commercially available polyisocyanate compounds are A-1310 and Y-5187 manufactured by Nippon Unicar Co., Ltd.; Calenz MOI manufactured by Showa Denko Co., Ltd.; TDI-80/20, TDI-100, MDI-CR100, MDI-CR300, MDI-PH, and NDI manufactured by Mitsui-Nisso Urethane Co., Ltd.; Coronate T, Millionate MT, Millionate MR, and HDI manufactured by Nippon Polyurethane Industry Co., Ltd.; and Takenate 600 manufactured by Takeda Chemical Industries Co., Ltd.

The amount of these polyisocyanate 15 compounds used in the above-mentioned method (a) is determined so that the ratio of the isocyanate group for one equivalent of the mercapto group in the mercaptoalkoxysilane is in the range from 0.1 to 100 equivalent, preferably from 0.5 to 10 equivalent, and 20 more preferably from 0.9 to 1.2 equivalent. If the amount of the polyisocyanate compounds in terms of the equivalence of isocyanate group is less than 0.1, 0.9 equivalent of mercaptosilane may be left unreacted, giving rise to insufficient abrasion resistance of 25 coating films. The use of polyisocyanate compounds in excess of 100 equivalent of isocyante group may leave a large amount of the isocyanate groups unreacted, resulting in the composition with lowered weather resistance. 30

In the above-mentioned method (b), on the

other hand, the amount of the polyisocyanate compounds in terms of the equivalenct of isocyanate group is in the range from 0.1 to 100, preferably from 0.5 to 10, and more preferably from 0.9 to 1.2, for one equivalent 5 of the active hydrogen contained in active hydrogencontaining polymerizable unsaturated compounds.

In either the method (a) or method (b), a catalyst can be added to shorten the reaction time. Either a basic catalyst or acid catalyst can be used as the catalyst. As examples of the basic catalyst, amines 10 such as pyridine, pyrrole, triethylamine, diethylamine, dibutylamine, and ammonia; phosphines such as tributyl phosphine and triphenyl phosphine; and the like can be given. Among these, tertiary amines such as pyridine and triethylamine are desirable. As acid catalysts, metal alkoxides such as copper naphthenate, cobalt naphthenate, zinc naphthenate, 1,4diazabicyclo[2.2.2]octane (DABCO), methyl DABCO, tributoxy aluminum, trititanium tetrabotoxide, and 20 zirconium tetrabotoxide; Lewis acids such as trifluoroboron diethyl etherate and aluminium chloride; tin compounds such as tin 2-ethylhexanoate, octyl tin trilaurate, dibutyl tin dilaurate, octyl tin diacetate, and the like can be given. Among these, acid catalysts are preferred, and tin compounds are particularly 25 preferred. Specific examples of particularly preferred tin compounds are octyl tin trilaurate, dibutyl tin dilaurate, octyl tin diacetate, and the like. The amount of these catalysts to be added is from 0.01 to 5 parts by weight, and preferably from 0.1 to 1 part by 30 weight, for 100 parts by weights of polyisocyanate

compounds. Effect of decrease in the reaction time is slight if the amount of the catalyst added is less than 0.01 part by weight. On the other hand, when the amount of the catalyst is more than 5 parts by weight, storage stability of the product may be impaired.

As examples of the active hydrogencontaining polymerizable unsaturated compound which can bind with the above-mentioned polyisocyanate compound through a urethane bond by the addition reaction in the preparation of the organosilicon 10 compound, the compounds having at least one active hydrogen atom which can form a urethane bond by the addition reaction with an isocyanate group and at least one polymerizable unsaturated group in the molecule can be given. These compounds can be used either 15 individually or in combinations of two or more. Carboxylic acid group-containing polymerizable unsaturated compounds and hydroxyl group-containing polymerizable unsaturated compounds are given as such 20 compounds. Specific examples of polymerizable unsaturated compound having a carboxylic acid group include unsaturated aliphatic carboxylic acid such as (meth) acrylic acid, itaconic acid, cinnamic acid, maleic acid, fumaric acid,

25 2-(meth) acryloxypropyl hexahydrogenphthalate, and 2-(meth) acryloxyethyl hexahydrogenphthalate; and unsaturated aromatic carboxylic acid such as 2-(meth) acryloxypropyl phthalate and 2-(meth) acryloxypropylethyl phthalate. Given as examples 30 of hydroxyl group-containing polymerizable unsaturated compounds are hydroxyl group-containing acrylates, hydroxyl group-containing methacrylates, and hydroxyl group-containing styrenes, such as 2-hydroxyethyl (meth)acrylate, 2-hydroxypropyl (meth)acrylate, 2-hydroxybutyl (meth)acrylate, 2- hydroxy-3-

- 5 phenyloxypropyl (meth)acrylate, 1,4-butanediol mono(meth)acrylate,
 - 2-hydroxyalkyl (meth)acryloyl phosphate, 4hydroxycyclohexyl (meth)acrylate, neopentyl glycol mono(meth)acrylate,
- poly(pentamethyleneoxycarboxylate)ethoxy
 (meth)acrylate,
 - hdroxy styrene, hydroxy α -methylstyrene, hydroxyethyl styrene, hydroxy-terminal polyethylene glycol styryl ether, hydroxy-terminal polypropylene glycol styryl
- ether, hydroxy-terminal polytetramethylene glycol styryl ether, terminal-hydroxy polyethylene glycol (meth)acrylate, terminal-hydroxy polypropylene glycol (meth)acrylate, terminal-hydroxy poly(tetraethylene glycol (meth)acrylate), trimethylolpropane
- di (meth) acrylate, pentaerythritol mono (meth) acrylate,
 dipentaerythritol penta (meth) acrylate,
 dipentaerythritol tetra (meth) acrylate,
 dipentaerythritol tri (meth) acrylate, dipentaerythritol
 di (meth) acrylate, and dipentaerythritol
- 30 mono(meth)acrylate.

Among these, unsaturated aliphatic

carboxylic acids and hydroxyl group-containing acrylate compounds are preferred, with the hydroxyl groupcontaining acrylate compounds, such as, for example, 2hydroxylethyl acrylate, 2-hydroxypropyl acrylate, pentaerythritol triacylate, and dipentaerythritol pentacrylate being particularly preferred. The amount of these active hydrogen-containing polymerizable unsaturated compound in terms of equivalent of the active hydrogen is one equivalent or more for one equivalent of isocyanate group remaining 10 in the intermediate compound which is produced by the addition reaction of a mercapto alkoxysilane and a polyisocyanate compound. If less than one equivalent, the resulting composition may exhibit undesirable effects such as foaming, viscosity increase, and 15 coloring due to the reaction of reactive isocyanate groups remaining in the alkoxysilyl compound and moisture.

In the preparation of the organosilicon compound, with an objective of improving flexibility of 20 coating films and increasing adhesion with substrates, a divalent organic group may be introduced by the addition reaction of a polyisocyanate compound between the alkoxysilyl group and the polymerizable unsaturated 25 group. As the organic compound which reacts with the isocyanate group by the addition reaction, a linear, cyclic, or branched organic compound having two or more active hydrogen atoms in the molecule can be used. Here, as examples of the group having active hydrogen atoms, a hydroxyl group, carboxyl group, mercapto 30 group, amino group, sulfonic group, phosphoric acid

group, silanol group, and the like can be given.

These organic compounds have two or more, preferably from 2 to 10, and more preferably 2, active hydrogen atoms in the molecule. The molecular weight of the compound having active hydrogen atoms is preferably from 50 to 100,000, more preferably from 100 to 50,000, and particularly preferably from 500 to 10,000. As examples of such a divalent organic compound, polyalkylene glycols, polyalkylene thioglycols,

10 polyalkylene diamines, polyalkylene dieleks,

- polyester diols, polyamides, polycarbonate diols, polyalkylene diamines, polyalkylene dicarboxylic acids, polyalkylene diols, and polyalkylene dimercaptans can be given. Among these, polyalkylene glycols are preferred. As examples of commercially available
- polyalkylene glycols, polyethylene glycol, polypropylene glycol, polytetraethylene glycol, polyhexamethylene glycol, and copolymers of two or more of these polyalkylene glycols can be given. Given as commercially available products are UNISAFE DC1100,
- UNISAFE DC1800, UNISAFE DCB1100, UNISAFE DCB 1800
 manufactured by Nippon Oil and Fats Co. Ltd., PPTG 4000
 , PPTG 2000, PPTG 1000, PTG 2000, PTG 3000, PTG 650,
 PTGL 2000, PTGL 1000 manufactured by Hodogaya Chemical
 Co., Ltd., and EXCENOL 1020 manufactured by Asahi Glass
- 25 Co., Ltd., PBG 3000, PBG 2000, PBG 1000, Z3001 manufactured by Daiichi Kogyo Seiyaku Co., Ltd. The methods for preparing the polymerizable unsaturated group-containing alkoxysilane containing the abovementioned divalent organic groups as the constituents
- will now be described taking polyalkylene glycol as an example of the divalent organic groups.

WO 00/27931 PCT/NL99/00678

Method (c):

A method comprising adding a polyalkylene glycol to the addition compound of a mercapto

5 alkoxysilane having a reactive isocyanate group at the terminal thereof and a polyisocyanate compound to convert the terminal hydroxyl group into an alkoxysilane group, and reacting the resulting compound with a separately prepared addition compound of the

10 polymerizable unsaturated compound having a hydroxyl group at the terminal thereof and a polyisocyanate compound to combine them via a urethane bond.

Method (d):

- A method of preparing an addition compound of a mercapto alkoxysilane having a reactive isocyanate group at the terminal thereof and a polyisocyanate compound, and reacting this addition compound with a separately prepared another addition compound of a polyalkylene glycol polyisocyanate compound having a reactive hydroxyl group at the terminal thereof and a hydroxyl group-containing polymerizable unsaturated compound, to combine these compounds via a urethane bond.
- 25 The conditions for forming the urethane bonds in the method (c) or method (d) are the same as the conditions used in the above-mentioned method (a) or (b). The equivalent ratio of the compound having a hydroxyl group at the terminal to the compound having a reactive isocyanate group at the terminal taking part in the bonding is in the range preferably from 1.0 to

1.2. If less than 1.0, coloring and viscosity increase due to unreacted isocyanate group tend to occur.

Moreover, a co-hydrolyzate with other organic alkoxysilane may be used as the hydrolyzate of a polymerizable unsaturated group-modified alkoxysilane in the preparation of the alkoxysilane compound. For example, a co-condensation product with other organic alkoxysilane such as an alkyl alkoxysilane, e.g. tetramethoxysilane, tetraethoxysilane,

- tetrabutoxysilane, methyltrimethoxysilane, methyltriethoxysilane, dimethyldimethoxysilane, phenyltrimethoxysilane, and the like may be used. When preparing the hydrolyzate, the amount of water used for the hydrolysis is usually from 0.5 to 1.5 equivalent
- for the amount of the total alkoxy group. A hydrolysiscondensation polymer can be obtained by stirring the reaction mixture for 5 minutes to 24 hours in the presence or absence of solvent, while heating at a temperature from 0 to the boiling point of the
- components. In this instance, an acid catalyst or base catalyst can be used to decrease the reaction time.

 The metal oxide particles used for preparing the component (B) are in the form of fine particles or a solvent dispersed sol. As a metal oxide, antimony
- oxide, zinc oxide, tin oxide, indium-tin mixed oxide, cerium oxide, aluminum oxide, titanium dioxide, and zirconium oxide can be given as examples. These may be used either individually or in combinations of two or more. In addition, from the viewpoint of ensuring
- 30 mutual solubility and dispersibility with the component A and mutual solubility with photo-initiators and

photosensitizers, a sol in a polar solvent such as alcohol, dimethylformamide, dimethylacetamide, or cellosolve may be used rather than water sol. As particularly preferred sols, sols of antimony oxide, zinc oxide, cerium oxide, and zirconium oxide can be given.

The average diameter of metal oxide particles is, for example, from 0.001 to 2 $\mu m.$ Such metal oxide particles can be commercially available 10 under the tradenames such as Alumina Sol-100, -200, -520 (alumina powder dispersed in water, manufactured by Nissan Chemical Industries, Ltd.), Celnax (zinc antimonate powder dispersed in water, manufactured by Nissan Chemical Industries., Ltd.), Nanotek (alumina, 15 titanium oxide, tin oxide, indium oxide, and zinc oxide powders dispersed in a solvent, manufactured by CI Chemical Co., Ltd.), Titania Sol, SN-100D (a sol of antimony dope tin oxide powder dispersed in water, manufactured by Ishihara Sangyo Kaisha, Ltd.), ITO 20 powder (manufactured by Mitsubishi Material Co., Ltd.), Needral (cerium oxide powder dispersed in water, manufactured by Taki Chemical Co., Ltd.), and the like. To prepare transparent films using the composition of the present invention, a preferable particle diameter is in the range from 0.001 to 2 μm , and more preferably 25 from 0.001 to 0.05 μm . The form of metal oxide particles may be spherical, hollow, porous, rod-like, plate-like, fibrous, or amorphous, and preferably spherical. The specific surface area of metal oxide particles is preferably from 10 to 3,000 m^2/g , and more 30 preferably from 20 to 1,500 m^2/g . These metal oxide

particles can be used as dry powder or as a dispersion in water or an organic solvent. Dispersions of fine particles of metal oxide well known in the art as solvent dispersion sols of metal oxide, for example,

5 can be used as they are. The use of a solvent dispersion sol of metal oxide is particularly desirable to ensure transparency. Organic solvents which can be used as a dispersion medium for metal oxide include methanol, isopropyl alcohol, ethylene glycol, butanol, ethylene glycol monopropyl ether, methyl ethyl ketone, methyl isobutyl ketone, toluene, xylene, dimethylformamide, and other solvents which are mutually soluble with these organic solvent, as well as mixtures of these organic solvents and water.

Preferable solvents are methanol, isopropyl alcohol, methyl ethyl ketone, xylene, and toluene.

The amount of alkoxysilane compound immobilized on the component (B) can be determined by measuring weight reduction (%) of the compound when fine dry particles are completely burnt in the air by a thermogravimetric analysis usually from roomtemperature to 800.

The amount of water which is consumed by
the hydrolysis of alkoxysilane compounds in the

25 preparation of the component (B) may be equivalent to
the amount of water to hydrolyze at least one alkoxy
group on a silicon atom in the molecule. The amount of
water to be added or present during the hydrolysis
reaction is preferably 1/3 or more, and more preferably

30 from 1/2 to 3 times, for the number of mols of the
total alkoxy group on the silicon atoms. Only a product

with the alkoxysilane compound physically adsorbed on the surface of the metal oxide particles can be obtained by merely blending the alkoxysilane compound of the above-mentioned formula (1) and metal oxide particles under the conditions where there is completely no water. The effect of increasing abrasion resistance which is one of the objectives of the composition of the present invention cannot be exhibited using such materials as the component (B).

5

10 The following methods can be used for preparing the component (B) of the present invention: a method comprising hydrolyzing the alkoxysilane compound of the above-mentioned formula (1), mixing the hydrolyzate with fine particles of metal oxide in the form of powder or a solvent dispersion sol, and 15 stirring the mixture with heating; a method of hydrolyzing the alkoxysilane compound of the abovementioned formula (1) in the presence of the metal oxide particles; a method of treating the surface of the metal oxide particles in the presence of other 20 components such as poly-functional unsaturated organic compounds, mono-functional unsaturated organic compounds, and photopolymerization initiators; and the like. Among these methods, a method of hydrolyzing the alkoxysilane compounds shown by the above-mentioned 25 formula (1) in the presence of metal oxide particles is preferred. In the preparation of the component (B), a temperature from 20 to 150 and the treating time in the range from 5 minutes to 24 hours are applied.

The metal oxide particles are known to contain moisture on the surface of the particles as

adsorbed water during normal storage conditions.

Therefore, it is possible to utilize the water

contained in the raw material in the preparation of the

component (B) by mixing the alkoxysilane compound and

metal oxide particles and stirring the mixture while

heating.

When a powder of metal oxide fine particles is used in the preparation of the component (B) of the present invention, an organic solvent which is mutually soluble with water may be added to carry out the 10 reaction of the powder of metal oxide fine particles with the alkoxysilane compound homogeneous and smoothly. As preferable examples of such an organic solvent, alcohols, ketones, ethers, and amides can be given. Given as specific examples are alcohols such as 15 methanol, ethanol, isopropyl alcohol, butanol, ethylene glycol monomethyl ether, and ethylene glycol monobutyl ether; ketones such as acetone, methyl ethyl ketone, and methyl isobutyl ketone; amides such as 20 dimethylformamide, dimethylacetamide, Nmethylpyrrolidone, γ -butyrolactone; and the like can be given. The amount of these solvents to be added is not specifically restricted inasmuch as such an amount conforms to the objective of carrying out the reaction 25 smoothly and homogeneously.

Moreover, an acid or a base may be added as a catalyst to accelerate the reaction for the preparation of the component (B). As examples of the acid, inorganic acids such as hydrochloric acid, nitric acid, sulfuric acid, and phosphoric acid; organic acids such as methane sulfonic acid, toluene

30

PCT/NL99/00678

sulfonic acid, phthalic acid, malonic acid, formic acid, acetic acid, and oxalic acid; unsaturated organic acids such as methacrylic acid, acrylic acid, and itaconic acid; and ammonium salts such as tetramethyl ammonium chloride and tetrabutyl ammonium chloride can be given. As examples of the base, aqueous ammonia; primary, secondary or tertiary aliphatic amines such as diethylamine, triethylamine, dibutylamine, and cyclohexylamine; aromatic amines such as pyridine; sodium hydroxide, potassium hydroxide, and quaternary 10 ammonium hydroxides such as tetramethylammonium hydroxide and tetrabutylammonium hydroxide can be given. Of these, preferable examples are organic acids and unsaturated organic acids among the acids, and 15 tertiary amines or tertiary ammonium hydroxides among

Any compounds which decompose upon irradiation of radioactive rays and initiate the polymerization can be used as the radiation polymerization initiator of the component (C) in the present invention. A photosensitizer may be added as required. The words 25 "radiation" as used in the present invention include infrared rays, visible rays, ultraviolet rays, deep ultraviolet rays, X-rays, electron beams, α -rays, β -

the bases. The amount of these acids or bases to be

added is preferably from 0.001 to 1.0 part by weight,

and more preferably from 0.01 to 0.1 part by weight,

for 100 part by weight of the alkoxysilane compounds.

20

Given as specific examples of the above-30 mentioned radiation polymerization initiators are acetophenone, acetophenone benzyl ketal, anthraquinone,

rays, γ-rays, and the like.

.

1-hydroxycyclohexylphenyl ketone, 2,2-dimethoxy-2-phenylacetophenone, xanthone compounds, triphenylamine, carbazole, 3-methylacetophenone, 4-chlorobenzophenone, 4,4'-dimethoxybenzophenone, 4,4'-diaminobenzophenone,

- 5 2-hydroxy-2-methyl-1-phenylpropan-1-one,
 - 1-(4-isopropylphenyl)-2-hydroxy-2-methylpropan-1-one,
 xanthone, 1,1-dimethoxydeoxybenzoin,
 - 3,3'-dimethyl-4-methoxybenzophenone, thioxanethone compounds, diethylthioxanthone, 2-
- isopropylthioxanthone, 2-chlorothioxanthone, 1-(4dodecylphenyl)-2-hydroxy-2-methylpropan-1-one, 2methyl-1-[4-(methylthio)phenyl]-2-morpholino-propan-1one, triphenylamine,
 - 2,4,6-trimethylbenzoyldiphenylphosphineoxide,
- bis-(2,6-dimethoxybenzoyl)-2,4,4trimethylpentylphosphine oxide, bisacylphosphineoxide,
 benzyl dimethyl ketal, fluorenone, fluorene,
 benzaldehyde, benzoin ethyl ether, benzoin propyl
 ether, benzophenone, Michler's ketone, 2-benzyl-2-
- dimethylamino-1-(4-morpholinophenyl)-butan-1-one, 3methylacetophenone, and 3,3',4,4'-tetra(tbutylperoxycarbonyl)benzophenone (BTTB). Combinations
 of BTTB and a coloring matter photosensitizer such as
 xanthene, thioxanthene, cumarin, or ketocumarin can
- also be given as specific examples of the initiator.

 Of these, benzyl dimethyl ketal, 1-hydroxycyclohexyl

 phenyl ketone, 2,4,6-trimethylbenzoyl diphenylphosphine

 oxide, bis-(2,6-dimethoxybenzoyl)-2,4,4-trimethylpentyl

 phosphine oxide, 2-benzyl-2-dimethylamino-1-(4-
- 30 morpholinophenyl)-butan-1-one, and the like are particularly preferred.

As examples of commercially available products of photoinitiators, Irgacure 184, 651, 500, 907, 369, 784, 2959, Darocur 1116, 1173 (manufactured by Ciba Specialty Chemicals Co., Ltd.), Lucirine TPO (manufactured by BASF), Ubecryl P36 (manufactured by UCB), and Escacure KIP150, KIP100F (manufactured by Lamberti) can be given.

As examples of photosensitizers, triethylamine, diethylamine, N-methyldiethanolamine, ethanolamine, 4-dimethylaminobenzoic acid, methyl 4-dimethylaminobenzoate, ethyl 4-dimethylaminobenzoate, and isoamyl 4-dimethylaminobenzoate, as well as commercially available products such as Ubecryl Pl02, 103, 104, 105 (manufactured by UCB), and the like can be given.

The proportion of the photoinitiators used as the component (C) in the composition of the present invention is in the range preferably from 0.01 to 10 wt%, more preferably from 0.5 to 7 wt%, and particularly preferably from 1 to 5 wt%. If more than 10 wt%, storage stability of the composition and properties of the cured products may be adversely affected. If less than 0.01 part by weight, on the other hand, a cure speed may be retarded.

25 Polymerizable monomers having a vinyl group or (meth)acryloyl group other than the above-mentioned component (A) can be used in the present invention as optional components. Such polymerizable monomers may be either mono-functional monomers or poly-functional monomers.

Given as examples of mono-functional

monomers are vinyl group-containing monomers such as N-vinyl caprolactam, N-vinyl pyrrolidone, N-vinylcarbazole, and vinylpyridine; acrylamide, acryloyl morpholine, 7-amino-3,7-dimethyloctyl (meth)acrylate,

- isobutoxymethyl (meth)acrylamide, isobornyloxyethyl (meth)acrylate, isobornyl (meth)acrylate, 2-ethylhexyl (meth)acrylate, ethyldiethylene glycol (meth)acrylate, t-octyl (meth)acrylamide, diacetone (meth)acrylamide, dimethylaminoethyl (meth)acrylate, diethylaminoethyl
- (meth)acrylate, lauryl (meth)acrylate,
 dicyclopentadiene (meth)acrylate,
 dicyclopentenyloxyethyl (meth)acrylate, dicyclopentenyl
 (meth)acrylate, N,N- dimethyl (meth)acrylamide,
 tetrachlorophenyl (meth)acrylate, 2-
- tetrachlorophenoxyethyl (meth)acrylate,
 tetrahydrofurfuryl (meth)acrylate, tetrabromophenyl
 (meth)acrylate, 2-tetrabromophenoxyethyl
 (meth)acrylate, 2-trichlorophenoxyethyl (meth)acrylate,
 tribromophenyl (meth)acrylate, 2-tribromophenoxyethyl
- 20 (meth)acrylate, 2-hydroxyethyl (meth)acrylate, 2hydroxypropyl (meth)acrylate, phenoxyethyl
 (meth)acrylate, butoxyethyl (meth)acrylate,
 pentachlorophenyl (meth)acrylate, pentabromophenyl
 (meth)acrylate, polyethylene glycol mono(meth)acrylate,
- polypropylene glycol mono(meth)acrylate, bornyl (meth)acrylate, and methyltriethylene diglycol (meth)acrylate.

Of these, N-vinyl caprolactam, N-vinyl pyrrolidone, acryloyl morpholine, N-vinylcarbazole,

isobornyl (meth)acrylate, phenoxyethyl (meth)acrylate, and the like are preferred, with N-vinyl caprolactam,

N-vinyl pyrrolidone, and acryloyl morpholine being particularly preferred. The most preferred monofunctional polymerizable monomer is acryloyl morpholine.

As examples of commercially available products of these mono-functional monomers, Aronix M-111, M-113, M-117 (manufactured by Toagosei Co., Ltd.), Kayarad TC110S, R-629, R-644 (manufactured by Nippon Kayaku Co., Ltd.), Viscoat 3700 (manufactured by Osaka Organic Chemical Industry Co., Ltd.), and the like can be given.

Given as examples of poly-functional monomers are (meth) acryloyl group-containing monomers such as ethylene glycol di(meth) acrylate,

- dicyclopentenyl di (meth) acrylate, triethylene glycol diacrylate, tetraethylene glycol di (meth) acrylate, tricyclodecanediyldimethylene di (meth) acrylate, tripropylene diacrylate, neopentyl glycol di (meth) acrylate, both terminal (meth) acrylate of
- ethylene oxide addition bisphenol A, both terminal (meth)acrylate of propylene oxide addition bisphenol A, both terminal (meth)acrylate of ethylene oxide addition tetrabromobisphenol A, both terminal (meth)acrylate of propylene oxide addition tetrabromobisphenol A,
- 25 bisphenol A diglycidyl ether, both terminal (meth)acrylate of tetrabromobisphenol A diglycidyl ether, 1,4-butanediol di(meth)acrylate, 1,6-hexanediol di(meth)acrylate, polyester di(meth)acrylate, and polyethylene glycol di(meth)acrylate.
- 30 Of these, both terminal (meth)acrylate of ethylene oxide addition bisphenol A, both terminal

(meth) acrylate of propylene oxide addition bisphenol A, tricyclodecanediyldimethylene di(meth) acrylate, tetraethylene glycol di(meth) acrylate, tripropylene glycol di(meth) acrylate, neopentyl glycol di(meth) acrylate, and polyethylene glycol di(meth) acrylate are preferred.

As commercially available products of polyfunctional monomers, Yupimer UV, SA1002 (manufactured by Mitsubishi Chemical Corp.), Viscoat 700 (manufactured by Osaka Organic Chemical Industry Co.

(manufactured by Osaka Organic Chemical Industry Co., Ltd.), Kayarad R-604 (manufactured by Nippon Kayaku Co., Ltd.), Aronix M-210 (manufactured by Toagosei Co., Ltd.), and the like can be used.

In addition to the above-described

components, various additives can be optionally added to the composition of the present invention. Given as examples of such additives are antioxidants, UV absorbers, light stabilizers, silane coupling agents, antioxidants, thermal polymerization inhibitors,

- coloring agents, leveling agents, surfactants, preservatives, plasticizers, lubricants, solvents, inorganic fillers, organic fillers, wettability improvers, coating surface improvers, and the like. As commercially available products of antioxidants
- Irganox 1010, 1035, 1076, 1222 (manufactured by Ciba Specialty Chemicals Co.), and the like can be given. As commercially available products of UV absorbers, Tinuvin P, 234, 320, 326, 327, 328, 213, 400 (manufactured by Ciba Specialty Chemicals Co.),
- 30 Sumisorb 110, 130, 140, 220, 250, 300, 320, 340, 350, 400 (manufactured by Sumitomo Chemical Industries Co.,

WO 00/27931

Ltd.), and the like are given. As commercially available products of light stabilizers, Tinuvin 292, 144, 622LD (manufactured by Ciba Specialty Chemicals Co.), Sanol LS-770, 765, 292, 2626, 1114, 744 (manufactured by Sankyo Chemical Co.), and the like can be given. As silane coupling agents, γ -aminopropyl triethoxysilane, γ -mercaptopropyltrimethoxysilane, γ methacryloxypropyltrimethoxysilane, and commercially available products such as SH6062, SZ6030 (manufactured by Dow Corning Toray Silicone Co., Ltd.), KBE903, KBM803 (manufactured by Shin-Etsu Silicone Co., Ltd.), and the like can be given. As commercially available products of aging preventives, Antigene W, S, P, 3C, 6C, RD-G, FR, AW (manufactured by Sumitomo Chemical Industries Co., Ltd.), and the like can be given. 15 Polymers or oligomers such as epoxy resins, polymerizable compounds (such as urethane (meth)acrylate, vinyl ether, propenyl ether, maleic acid derivatives), polyamide, polyimide, 20 polyamideimide, polyurethane, polybutadiene, chloroprene, polyether, polyester, pentadiene derivatives, styrene/butadiene/styrene block copolymer, styrene/ethylene/butene/styrene block copolymer, styrene/isoprene/styrene block copolymer, petroleum 25 resin, xylene resin, ketone resin, fluorine-containing oligomers, silicon-containing oligomers, polysulfidetype oligomers can also be incorporated in the composition of the present invention as other

The radiation curable resin composition of the present invention can produce cured products with

additives.

excellent characteristics such as a high refractive index, superior abrasion resistance, transparency, chemical resistance, and the like. The composition is thus suitable for use as a hard coat for plastic optical parts, touch panels, and film-type liquid crystal elements, and fabricated plastic materials, and also as a stain-proof or mar-proof coating material for floors and walls inside buildings. In addition, because the composition does not produce interference fringes 10 when applied to a substrate with a similar refractive index due to its high refractive index, the composition can be used suitably in optical applications. When the radiation curable resin composition of the present invention is cured, cured products with pencil hardness from H to 9H at 23 can be obtained. The rate 15 of shrinkage upon curing is usually 10% or less, and preferably 6% or less. As mentioned above, the resulting cured products has a high refractive index, excellent abrasion resistance, transparency, chemical resistance, and the like. The cured products has 20 preferably a refractive index of 1.55 or more and light transmittance of 98% or more. Also, preferably an about 5 μm thick layer of the composition, after cure, will have a light transmittance of at least 90%, and, after the Taber's abrasion test that is set forth in this 25 application, haze value of less than 40%. Therefore, the composition can be suitably used for plastic sheets, plastic films, and the like requiring transparency, and particularly as materials for optical use. Other application of the composition includes 30 cathode-ray tubes and front panels such as a flat

WO 00/27931 PCT/NL99/00678

display, laser display, photochromic display, electrochromic display, liquid crystal display, plasma display, light emitting diode display, and electroluminescent panel, as well as parts for input equipment of these front panels. Other application includes front covers such as an enclosure case, lens for optical instrument, eye glass lens, window shield, light cover, helmet shield, and the like. In addition, when a coating with a high refractive index is used as an optical material, it is desirable to provide a coating with a low refractive index to prevent reflection.

Examples

The present invention will now be described in more detail by way of examples which should not be construed as limiting the present invention. In the following examples, unless otherwise indicated, "parts" and "%" means respectively "parts by weight" and "wt%".

20

25

30

10

Preparation of alkoxysilane compound Reference Example 1

added dropwise to a solution consisting of 7.8 parts of mercaptopropyl trimethoxysilane and 0.2 part of dibutyl tin dilaurate over one hour while stirring in dry air at 50. After stirring for a further 3 hours at 60, 71.4 parts of pentaerythritol triacylate was added dropwise over one hour at 30. The mixture was stirred for an additional 3 hours with heating at 60 to obtain a compound having a polymerizable unsaturated group and

alkoxysilane group in the molecule. This compound is herein designated as "silane compound X". The amount of residual isocyanate group in the product was analyzed. It was confirmed that the amount of residual isocyanate group was 0.1% or less, indicating that the reaction was completed almost quantitatively.

PCT/NL99/00678

Preparation of the component (B)

Reference Example 2

A mixture of 8.1 parts of the silane 10 compound X prepared in Reference Example 1, 90.5 parts of zirconium oxide sol in methyl ethyl ketone solvent (number average particle diameter: 0.01 μm , zirconium oxide concentration: 30%), and 0.1 part of ion exchanged water was stirred for three hours at 60. 15 After the addition of 1.3 parts of methyl orthoformate and 41.2 parts of methyl ethyl ketone, the mixture was stirred for a further one hour while heating at the same temperature to obtain a dispersion liquid of the reaction product of the compound having a polymerizable 20 unsaturated group and alkoxysilane group in the molecule and particles of zirconium. This dispersion liquid is herein designated as "dispersion bl".

Reference Example 3

A mixture of 8.1 parts of the silane compound X prepared in Reference Example 1, 90.5 parts of antimony pentoxide sol in methyl ethyl ketone solvent (number average particle diameter: 0.05 μm , 5 antimony pentoxide concentration: 30%), and 0.1 part of ion exchange water was stirred for three hours at 60. After the addition of 1.3 parts of methyl ortho-formate and 41.2 parts of methyl ethyl ketone, the mixture was stirred for a further one hour while heating at the same temperature to obtain a dispersion liquid of the reaction product of the compound having a polymerizable unsaturated group and alkoxysilane group in the molecule and particles of antimony pentoxide. This dispersion liquid is herein designated as "dispersion b2". A solid content (%) of this dispersion liquid was 25%.

Reference Example 4

10

15

A mixture of 8.1 parts of the silane compound X prepared in Reference Example 1, 100 parts of alumina sol in methanol (number average particle diameter: 0.0075 μm, solid content: 30%, water content: 5.6%), and 0.01 part of p-methoxy phenol was stirred for three hours at 60. After the addition of 1.3 parts of methyl orthoformate and 41.2 parts of methanol, the mixture was stirred for a further one hour while heating at the same temperature to obtain a dispersion liquid of the reaction product of the compound having a polymerizable unsaturated group and alkoxysilane group in the molecule and alumina particles. This dispersion

liquid is herein designated as "dispersion b3". A solid content (%) of this dispersion liquid was 25%.

Preparation of compositions

Preparation of the composition used in the present invention will now be described. The ratio by weight of each component is shown in Table 1.

Example 1

- 10 80 parts of the dispersion liquid bl prepared in Reference Example 2 as the component (B), 20 parts of dipentaerythritol hexacrylate as the component (A), 1.2 parts of 1-hydroxycyclohexyl phenyl ketone and 0.8 parts of 2-methyl-1-[4-
- 15 (methylthio)phenyl]-2- morpholinopropan-1-one as the component (C) were placed in a container shielded from ultraviolet rays and the mixture was stirred for 30 minutes at room-temperature to obtain the composition shown in Table 1 as a homogeneous solution. The
- compositions for Example 2-5 and Comparative Examples
 1-3 shown in Table 1 were prepared in the same manner.
 The compositions of Examples 1 and 3 correspond to the compositions of Comparative Examples 2 and 3 respectively. The compositions of Examples 2 and 4 and
- 25 Comparative Example 1 contain a large amount of the component (B) to increase the refractive index.

TABLE 1
Parts (parts of solid components)

	Example	e e				Сошра	Comparative		
						Example	le		
	1	2	3	4	5	Н	2	3	·
Component (A)									
Unsaturated organic compound	20	ω	20	12	12		20	20	
(Dipentaerythritol hexacrylate)									
Metal oxide sol solution without silane									
treatment									
Zirconia sol							80	1	
							(20)		_
Antimony oxide sol								80	·
		•						(20)	

) (32) 80 (20) (20) 1.2 1.2 0.8 0.8				
### ##################################				
(20) (32) 80 88 mponent (C). *1-hydroxycyclohexyl phenyl ketone 1.2 1.2 1.2 1.2 1.2				
mponent (C). *1-hydroxycyclohexyl phenyl ketone *2-methyl-1-[4-(methylthio)phenyl]-2- *2-methyl-1-one morpholinopropan-1-one tal		100		
#1-hydroxycyclohexyl phenyl ketone 1.2 1.2 1.2 1.2 1.2 1.2 morpholinopropan-1-one 102 102 102 102 102 102 102 102 102 102		(40)		_
#1-hydroxycyclohexyl phenyl ketone 1.2				
*1-hydroxycyclohexyl phenyl ketone 1.2 1.2 1.2 1.2 1.2 1.2 1.2 1.2 methyl-1-[4-(methylthio)phenyl]-2- 0.8 0.8 0.8 0.8 morpholinopropan-1-one 102 102 102 102 102				
(C). xycyclohexyl phenyl ketone 1.2 1.2 1.2 1.2 yl-1-[4-(methylthio)phenyl]-2-[0.8] 0.8 0.8 0.8 0.8 inopropan-1-one 102 102 102 102		0.	· · · · · · · · · · · · · · · · · · ·	
(C). (xycyclohexyl phenyl ketone 1.2 1.2 1.2 1.2 1.2 1.2 1.2 1.2 1.2 1.2		(20)		
-hydroxycyclohexyl phenyl ketone 1.2 1.2 1.2 1.2 1.2 1.2 1.2 1.2				
-methyl-1-[4-(methylthio)phenyl]-2- 0.8 0.8 0.8 0.8 rpholinopropan-1-one 102 102 102 102	1.2 1.2 1.2	1.2	1.2 1.2	~
rpholinopropan-1-one 102 102 102 102	0.8 0.8 0.8	8.0	0.8 0.8	
102 102 102			· . · · · · · · · · · · · · · · · · · ·	
	102 102 102 102 9	102	102 102	2
Solid components (%) 41 41 41 36	41 41 41	41	41 41	
Metal oxide in the solid components 38 61 38 53 46	61 38 53	76	50 50	
(wt%)				

Test Examples

Test specimens were prepared using the resin compositions prepared in the above Examples and Comparative Examples to evaluate pencil hardness, mar resistance, abrasion resistance, adhesion to substrates, transmittance, and refractive index of the cure films according to the following methods. The results are shown in Table 2.

Preparation of test specimens:

The resin compositions prepared in the above Examples and Comparative Examples were applied on a commercially available PET film (thickness: 188 μ m) using a wire bar coater (No. 10) to a thickness of about 5 μ m. The coatings were allowed to stand for one minute in an infrared dryer oven at 40, followed by irradiation with ultraviolet rays at a dose of 0.3 J/cm^2 in the air to obtain cured coating films. The cured films were then allowed to stand at 23 and relative humidity of 50% for 24 hours to obtain test specimens.

Appearance:

The appearance was evaluated by naked eye observation.

Light transmittance:

Light transmittance at a wavelength of 500 nm was measured using a spectrophotometer and corrected for reflectance and transmittance of the substrates.

Refractive index:

The refractive index was measured by Abbe's refractometer.

Pencil hardness:

The pencil hardness was measured according to JIS K5400 using a pencil scratch tester.

Abrasive resistance:

A haze value (H) after the Taber's abrasion test (abrasive wheel CS-10F, load 500 g, rotation 100) was measured using a Taber's abrasion tester according to JIS R3221.

Substrate adhesion:

JIS K5400 was followed. 100 squares (1 mm \times 1 mm) were produced on the surface of the cured test specimen by 11 \times 11 cross-cut lines. A commercially available cellophane tape was adhered and rapidly peeled off. The substrate adhesion was indicated by \times 100, wherein \times 1 is the number of squares left on the substrate without being detached.

(`	1	
•	•	1	
Ē	1	•	

	Example					Compara	Comparative Example	le	J/2 /93
		2	3	4	5	П	2	3	
Appearance	Trans-	Trans-	Trans-	Trans-	Trans-	Trans-	Semi-	Opaque	
	parent	parent	parent	parent	parent	parent	transpa-		
	·						rent		
Light transmittance (/%)	66	66	100	100	97	100	89	63	
Refractive index	1.595	1.645	1.555	1.566	1.560	1.585	1.641	-	
Pencil hardness	3Н	2H	3Н	2Н	3H	Н	3Н	3H	-44
<pre>Haze value of coating film (%)</pre>	0.5	9.0	0.5	0.5	0.6	9.0	4.4	6.8	
1-0									
Taber's test *	28	22	28	31	8	49	27	46	
Adhesion **	100	100	100	100	100	100	100	100	

* Haze value (%)

** Number of cross-cut squares (%) after cellophane tape detachment.

The radiation curable resin composition of the present invention can produce cured products with excellent characteristics such as a high refractive index, superior abrasion resistance, transparency, chemical resistance, and the like. The composition is thus suitable for use as a hard coat for plastic optical parts, touch panels, and film-type liquid crystal elements, and fabricated plastic materials, and also as a stain-proof or mar-proof coating material for 10 floors and walls inside buildings. In addition, because the composition does not produce reflection interference stripes when applied to a substrate with a similar refractive index due to its high refractive index, the composition can be used suitably in optical 15 applications.

CLAIMS

- A radiation-curable metal particle comprising a 1. radiation-curable group linked by a silyl group to a metal. 5
 - The particle according to claim 1, wherein said 2. metal is selected from the group consisting of zirconium, tatinium, antimony, zinc, tin, indium, cerium and aluminium.
- The particle according to any one of claims 1-2, 10 3. wherein the silyl group is a substituted silyl group which comprises an alkoxy group, a urethane group and/or a thiourethane group.
- The particle according to any one of claims 1-3, 4. wherein said particle is obtainable by reacting 15 an organosilicon compound with a metal oxide.
 - The particle according to any one of claims 1-4, 5. wherein the particle has a diameter of from 0.001 to 2 μm.
- A method for forming a radiation-curable metal 6. 20 particle according to any one of claims 1-5, comprising reacting a metal oxide with an organosilicon compound.
- The method according to claim 6, wherein the 7. metal oxide is reacted with the organosilicon 25 compound in the presence of an acid or a base.
 - A radiation-curable composition comprising: 8.
 - (A) a (meth)acrylic compound;
 - (B) metal particles according to any one of claims 1-6; and
 - (C) a radiation polymerization photoinitiator.



30

WO 00/27931 PCT/NL99/00678

9. The composition according to claim 8, wherein said (meth) acrylic compound comprises at least three (meth) acryloyl groups.

- The composition according to any one of claims 8-9, wherein an about 5 μm thick layer of the composition, after cure, has a light transmittance of at least 90% and a haze value after the Taber's abrasion test of less than 40%.
- 11. A product formed from curing the composition

 10 according to any one of claims 8-10, wherein said product has a refractive index of at least 1.55 and a light transmittance of at least 95%.
 - 12. The product according to claim 11, wherein said products is a coating.
- 15 13. An anti-reflection article comprising the product according to any one of claims 11-12.

tritex onal Application No PCT/NL 99/00678


A CLASSIFICATION OF SUBJECT MATTER IPC 7 C09C3/12 C08K C08K9/06 G02B1/11 According to international Patent Classification (IPC) or to both national classification and IPC B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) IPC 7 C09C G02B C08K Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched Electronic data base consulted during the international search (name of data base and, where practical, search terms used) C. DOCUMENTS CONSIDERED TO BE RELEVANT Category * Citation of document, with indication, where appropriate, of the relevant passages Relevant to claim No. X US 4 624 971 A (VAN TAO NGUYEN ET AL) 1-13 25 November 1986 (1986-11-25) the whole document US 4 778 834 A (MURRAY DOUGLAS G) X 1,8 18 October 1988 (1988-10-18) column 6, line 38 -column 7, line 5 X US 5 277 980 A (MINO NORIHISA) 1 11 January 1994 (1994-01-11) claims X US 4 169 912 A (AMBROS OTTO ET AL) 1,3-7 2 October 1979 (1979-10-02) examples X Further documents are listed in the continuation of box C. Patent family members are listed in annex. Special categories of cited documents: T later document published after the international filing date or priority date and not in conflict with the application but "A" document defining the general state of the art which is not considered to be of particular relevance cited to understand the principle or theory underlying the Invention earlier document but published on or after the International "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered it filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such docu-"O" document referring to an oral disclosure, use, exhibition or ments, such combination being obvious to a person skilled in the art. other means document published prior to the international filing date but inter then the priority date claimed "&" document member of the same patent family Date of the actual completion of the international search Date of mailing of the international search report . 14 February 2000 24/02/2000 Name and mailing address of the ISA Authorized officer European Patent Office, P.B. 5818 Patentiaan 2 NL - 2290 HV Pitentik Tel. (+31-70) 340-2040, Tx. 31 651 epo ni, Fax: (+31-70) 340-3018 Meulemans, R

7



Inte. onel Application No PCT/NL 99/00678

		PC1/NL 99/00076	
C.(Continue	ntion) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to daim No.	
(US 4 167 423 A (WILLIAMS THOMAS C) 11 September 1979 (1979-09-11) claim 1	1,3-7	
(US 4 213 886 A (TURNER ROBERT L) 22 July 1980 (1980-07-22) claims	1,8	
	US 5 618 872 A (POHL LUDWIG ET AL) 8 April 1997 (1997-04-08) column 4, line 28-54 column 4, line 44,45	1-7	
(US 5 494 949 A (KINKEL JOACHIM ET AL) 27 February 1996 (1996-02-27) the whole document	1-7	
	-		



information on patent family members

trite onel Application No PCT/NL 99/00678

					· · · · · · · · · · · · · · · · · · ·
Patent door cited in searc		Publication date		Patent family member(s)	Publication date
US 46249	71 A	25-11-1986	AT	12944 T	15-05-198!
			WO	8202403 A	22-07-1982
			ËP	0069133 A	12-01-1983
			ĴΡ	58500251 T	
			JP		17-02-1983
			Ur	62021815 B	14-05-1987
US 47788	34 A	18-10-1988	NON	E	
US 52779	80 A	11-01-1994	JP	1957297 C	10-08-1995
			JP	2225534 A	07-09-1990
			JP	6086535 B	02-11-1994
			JP	1309902 A	14-12-1989
			JP	1977536 C	17-10-1995
			JP	7005924 B	25-01-1995
•			JP	1986668 C	08-11-1995
			JP	2009196 A	12-01-1990
			JP	7019947 B	06-03-1995
			DE		
				68924198 D	19-10-1995
			DE	68924198 T	21-03-1996
			EP	0346074 A	13-12-1989
			US	4985273 A	15-01-1991
US 41699	12 A	02-10-1979	DE	2543962 A	14-04-1977
			BE	846849 A	31-01-1977
			FR	2326454 A	29-04-1977
			GB	1547636 A	27-06-1979
			IT	1069992 B	25-03-1985
			ĴΡ	52044794 A	08-04-1977
			NL	7610900 A	05-04-1977
			US	4271234 A	02-06-1981
US 416742	23 A	11-09-1979	CA	1067762 A	11-12-1979
			CH	615896 A	2 9- 02-1980
			DE	2524863 A	11-12-1975
			DE	2559639 A	12-05-1977
			FR	2346420 A	28-10-1977
			FR	2292748 A	25-06-1976
			GB	1507745 A	19-04-1978
			ĬŤ	1038686 B	30-11-1979
			ĴP	1014490 C	25-09-1980
			JP	51006898 A	
			JP	55005548 B	20-01-1976
					07-02-1980
			SE	415028 B	01-09-1980
			SE	7506413 A	08-12-1975
	6 A	22-07-1980	NONE		
US 421388				1010007	
US 421388 US 561887	'2 A	08-04-1997	DE	4219287 A	16-12-1993
	'2 A	08-04-1997			
	'2 A	08-04-1997	AT	186061 T	15-11-1999
	'2 A	08-04-1997	AT DE	186061 T 59309852 D	15-11-1999 02-12-1999
	'2 A	08-04-1997	AT De Wo	186061 T 59309852 D 9325611 A	15-11-1999 02-12-1999 23-12-1993
	'2 A	08-04-1997	AT DE WO EP	186061 T 59309852 D 9325611 A 0644914 A	15-11-1999 02-12-1999 23-12-1993 29-03-1995
US 561887			AT De Wo	186061 T 59309852 D 9325611 A	15-11-1999 02-12-1999 23-12-1993
US 561887		08-04-1997 27-02-1996	AT DE WO EP JP	186061 T 59309852 D 9325611 A 0644914 A 7507823 T	15-11-1999 02-12-1999 23-12-1993 29-03-1995
US 561887			AT DE WO EP JP	186061 T 59309852 D 9325611 A 0644914 A 7507823 T	15-11-1999 02-12-1999 23-12-1993 29-03-1995 31-08-1995 07-04-1994
			AT DE WO EP JP	186061 T 59309852 D 9325611 A 0644914 A 7507823 T	15-11-1999 02-12-1999 23-12-1993 29-03-1995 31-08-1995



INTERNATIONAL SEARCH REPORT

information on patent family members

PCT/NL 99/00678

Patent document cited in search report	Publication date		atent family member(s)	Publication date
US 5494949 Å		WO	9407945 A	14-04-1994
		EP	0663933 A	26-07-1995
		EP	0615531 A	21-09-1994
		JP	7502301 T	09-03-1995
		JP	8501818 T	27-02-1996
		ÜS	5698309 A	16-12-1997

THIS PAGE BLANK (COPTO)